

OFFER: Clinker

Origin: Pakistan

Packaging: in bulk

Production capacity: 50,000 MT per month

Standard: British 12/1996

Time	Kiln Feed CaCO ₃	Clinker Lt / Weight	Average clinker analysis	
9.00	Stop	Stop	SiO ₂	21.66
10.00	-	-	Al ₂ O ₃	4.47
11.00	-	-	Fe ₂ O ₃	3.48
12.00	-	-	CaO	64.22
1.00	-	-	MgO	3.60
2.00	77.93	1250	SO ₃	0.70
3.00	78.43	1350	LSF	0.92
4.00	78.43	1250	SM	2.72
5.00	77.43	1300	AM	1.28
6.00	77.68	1300	C ₃ S	55.58
7.00	77.93	1250	C ₂ S	20.26
8.00	77.43	*1200	C ₃ A	5.96
9.00	77.19	*1200	C ₄ AF	10.59
10.00	76.69	*1200	Lt/Wt	1250
11.00	77.40	*1250	CaO	1.04
12.00	77.19	*1200	LP	25.54
1.00	77.69	*1200		
2.00	78.19	*1200		
3.00	77.44	*1200		
4.00	77.94	*1200		
5.00	77.68	1250		
6.00	77.40	1250		
7.00	77.19	1250		
8.00	77.43	*1200		
Average:	77.62	1250		

Compressive strength

3 days	7 days	28 Days
3535 (Disp) Slag	4506 (Disp) Slag	-
3650 (Disp) OPC	4738 (Disp) OPC	-